

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification⁶ : B01J 38/60, 23/96	A1	(11) International Publication Number: WO 99/67023 (43) International Publication Date: 29 December 1999 (29.12.99)
(21) International Application Number: PCT/NL99/00389 (22) International Filing Date: 24 June 1999 (24.06.99) (30) Priority Data: 98202127.1 25 June 1998 (25.06.98) EP (71) Applicant (for all designated States except US): ENGELHARD CORPORATION [US/US]; 101 Wood Avenue, Iselin, NJ 08830-0770 (US). (72) Inventor; and (75) Inventor/Applicant (for US only): VAARKAMP, Marius [NL/NL]; Vleutenseweg 399, NL-3532 HH Utrecht (NL). (74) Agent: OTTEVANGERS, S., U.; Vereenigde Octrooibureaux, Nieuwe Parklaan 97, NL-2587 BN The Hague (NL).		(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: PROCESS FOR REGENERATING A USED PRECIOUS METAL CATALYST (57) Abstract The invention is directed to a process for the regeneration of a catalyst, said catalyst comprising at least one precious metal on an amorphous silica-alumina support, in which process the catalyst is impregnated with an acid, followed by reduction or oxidation of the impregnated catalyst at a temperature above 200 °C.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

Title: Process for regenerating a used precious metal catalyst

The present invention is directed to a process for regenerating a used precious metal catalyst by redispersing the precious metal. Regeneration of used precious metal catalysts is an important aspect of this type of catalyst technology, intended to extend the lifetime of the precious metal catalyst. Regeneration is generally performed in three steps, namely 1) Removal of carbonaceous deposits (usually by burning), 2) redispersion of the precious metal, and 3) reduction of the redispersed precious metal.

Various methods for regeneration of used precious metal catalyst by redispersion of the precious metal on the support are known. Generally the redispersion is done by treatment with oxygen, Cl_2 or Br_2 .

In a review article of J.B. Butt and E.E. Petersen in Activation, Deactivation and Poisoning of Catalyst, Academic Press (1988), pp 214 to 232, it has been indicated that the following general types of redispersion procedures have been suggested: 1) thermal treatment in an oxygen atmosphere, 2) thermal treatment in oxygen followed by reduction in hydrogen, 3) high temperature treatment followed by rapid cooling or 4) chemical dissolution of contaminants and redispersion of the metal. In this article it has been indicated that the behaviour of a catalyst in redispersion experiments is very much dependent on the nature of the support. A platinum on alumina catalyst can for example be redispersed using air, whereas platinum on silica behaves totally different.

In WO-A 95/23643 a process has been described for the catalytic treatment of waste water, using a precious metal catalyst, which process includes as part of the overall process the regenerating of the catalyst. The regeneration of the catalyst which is a palladium on silica/carbon, is done

by washing with an organic solvent, and/or acid and/or by thermal treatment.

In US-A 3,804,777 a process has been described, wherein lead contaminants present in a precious metal catalyst are dissolved by percolating a dilute acid at ambient temperature through the catalyst, followed by treatment with hydrogen at about 100°C.

The present invention deals with a process for regenerating a precious metal catalyst on an amorphous silica alumina support. The inventors of the present invention have found that the conventional methods, for example such as reported by Butt et al, but also the methods using chlorine or bromine do not result in an increase of dispersion, as will be shown in the examples to be reported herein. Various known methods result in a decrease of the degree of dispersion.

It is an object of the present invention to provide a method for redispersing the precious metal present in a catalyst based on an amorphous silica-alumina support.

The process according to the present invention for the regeneration of a catalyst, said catalyst comprising at least one precious metal on an amorphous silica alumina support, comprises impregnating the catalyst with an acid, followed by reduction or oxidation of the impregnated catalyst at a temperature above 200°C.

The regeneration of the catalyst, as used herein, indicates a redispersion of the said at least one precious metal over the surface of the support.

Surprisingly it has been found that the use of an acid in a liquid state, such as an aqueous solution, followed by the specific thermal treatment results in a redispersion of the precious metal on the support, whereas other methods result in a decrease of the degree of dispersion.

Suitable precious metals for use in the catalyst to be regenerated by the process according to the present invention are platinum, palladium, gold, iridium, rhenium,

ruthenium, rhodium, osmium and silver. Also combinations of two or more of those precious metals can be used. So it is possible to use a combination of at least one of those precious metals with one or more other metals. The preferred catalyst to be regenerated by the process of the present invention is based on platinum and/or palladium.

The precious metal catalysts to be regenerated by the process of the present invention have generally been used for reactions involving hydrogenation, such as hydrogenation itself, hydro-isomerisation, hydro-desulfurisation and hydro-dewaxing. They may also have been used in dehydrogenation reactions, such as catalytic reforming. Once the performance of the catalyst decreases below a certain level the catalyst is regenerated. In some processes it is also usual to perform regeneration simply after a certain amount of time has passed, without waiting for a decrease of the activity.

The catalyst to be regenerated is, either in the reactor or in a separate plant, prepared for the actual redispersion experiment. This step includes the removal of carbonaceous deposits and other unwanted material on the catalyst. This can for example be done by washing using a suitable solvent and/or by burning of the contaminants.

Subsequently the catalyst is impregnated with an acid, preferably in an aqueous solution. Suitable acids are the usual mineral acids, including HCl, H_3PO_4 , H_2SO_4 , HNO_3 , HBr, or combinations of two or more of these acids. The amount of acid on the basis of the ratio of equivalents of acid to atoms of precious metal is between 0.1 and 100, preferably between 0.5 and 10. After impregnating the catalyst with the acid, the impregnated catalyst is either reduced in a flow of hydrogen gas or oxidised in a flow of dry air, followed by reduction. In a more preferred embodiment both reduction and oxidation are carried out at a temperature of at least 250°C and more in particular between 250°C and 600°C.

After the final reduction step a supported catalyst is obtained usually having approximately the same degree of dispersion as the original catalyst. Sometimes the treatment even results in an increase of degree of dispersion. It is to be noted in this respect that the degree of dispersion is related to the precious metal crystallite size. The degree of dispersion can for example be determined by CO-chemisorption, whereby the amount of CO absorbed by the precious metal gives an indication of the number of metal atoms available on the surface of the metal crystallites. A larger amount of chemisorbed CO indicates a higher degree of dispersion, i.e. a smaller metal crystallite size.

An important aspect of the present invention resides therein that the catalyst to be regenerated is based on an amorphous silica alumina support. On the support a precious metal is present preferably in an amount of from 0.001 to 5 wt.%, calculated on the weight of the catalyst (in reduced form). The amorphous silica-alumina support is preferably prepared using a sol-gel method, whereas the support has an Si/Al atomic ratio of between 0.1 and 300. As has been indicated before, the type of support is extremely important in the selection of the regeneration method.

The present invention is now elucidated on the basis of a number of experiments.

EXAMPLES

In the examples the effect of various treatments on the dispersion of 0.7 wt.% platinum on a silica-alumina support having an Si/Al atomic ratio of 8 is shown. The catalyst support is prepared by a sol-gel method as for example described in International patent application PCT/NL98/00090. The fresh catalyst had an CO/Pt ratio of 0.25, which is a measure for the degree of dispersion of the precious metal.

Samples of this catalyst were subjected to various treatments, which are described in the subsequent table, together with the result thereof.

5 Table 1 Redisperison experiments for Pt/silica-alumina

treatment	CO/Pt
none	0.25
air 400°C	0.25
air 500°C	0.23
500°C, 0.8% Cl, 5% H ₂ O, 2h	0.12
530°C, 0.8% Cl, 5% H ₂ O, 4h	0.07
530°C, 0.8% Cl, 5% H ₂ O, 2h	0.07
HCl imp, dry air 400°C	0.31
HCl imp, H ₂ 300°C	0.33
HCl imp, wet air 400°C	0.07
HCl imp, wet HCl 200°C	0.12

10 As can be seen from this table, treatment with air had almost no influence, whereas treatment with a gas flow containing chlorine and water strongly decreased the dispersion. Also impregnating with hydrochloric acid, followed by wet air or wet hydrochloride at increased
15 temperature resulted in a strong decrease of degree of dispersion. Only acid impregnation followed by treatment with dry air and hydrogenation, or acid impregnation followed by hydrogenation only, showed an improvement in the degree of dispersion.

Claims

1. Process for the regeneration of a catalyst, said catalyst comprising at least one precious metal on an amorphous silica-alumina support, in which process the catalyst is impregnated with an acid, followed by reduction or oxidation of the impregnated catalyst at a temperature above 200°C.
2. Process according to claim 1, wherein the precious metal is at least one of Pt, Pd, Au, Ir, Ru, Rh, Re, Os and Ag, preferably Pt and/or palladium.
- 10 3. Process according to claim 1 or 2, wherein the degree of dispersion is increased after the regeneration.
4. Process according to claims 1-3, wherein the acid impregnated catalyst is reduced in a flow of hydrogen gas.
5. Process according to claims 1-4, wherein the acid impregnated catalyst is oxidised in a flow of dry (<0.1 vol.% of water) air, followed by reduction.
- 15 6. Process according to claims 1-5, wherein the reduction and or oxidising step are carried out at a temperature of between 250 and 600°C.
- 20 7. Process according to claims 1-6, wherein the silica-alumina support has been prepared using a sol-gel method.
8. Process according to claims 1-7, wherein the support has an Si-Al atomic ratio of from 0.1 to 300.
9. Process according to claims 1-8, wherein the catalyst has a precious metal content of from 0.01 to 5 wt.%, calculated on the basis of the weight of reduced catalyst.
- 25 10. Process according to claims 1-9, wherein the catalyst is impregnated with an aqueous solution of the acid.
11. Process according to claims 1-10, wherein the acid is selected from the group of HCl, H₃PO₄, H₂SO₄, HNO₃, HBr and combinations thereof.
- 30

12. Process according to claims 1-11, wherein the amount of acid calculated on the basis of a ratio of equivalents of acid to atoms of precious metal is between 0.1 and 100, preferably between 0.5 and 10.
- 5 13. Process according to claims 1-12, wherein prior to the impregnation, carbonaceous deposits on the catalyst are burned off.
14. Process according to claim 1-13, wherein the regeneration is carried out in a reactor, separate from the
10 reactor in which the catalyst is used.
15. Process according to claims 1-14, wherein the catalyst is a used catalyst from a process in the group consisting of hydrogenation, hydro-isomerisation, hydro-desulfurisation, hydrodewaxing and catalytic reforming.
- 15 16. Process for hydrogenation, hydro-isomerisation, hydro-desulfurisation or hydrodewaxing, comprising treating the feedstock in the presence of a catalyst that has been regenerated using the process of claims 1-15.

INTERNATIONAL SEARCH REPORT

National Application No

EUR/NL 99/00389

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 B01J38/60 B01J23/96

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 B01J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 3 804 777 A (CANAVESI R ET AL) 16 April 1974 (1974-04-16) claims 1,2 column 1, line 30 - line 34	1,2, 9-11, 14-16
Y	---	6
Y	FR 2 325 289 A (INST FRANCAIS DU PETROL) 15 April 1977 (1977-04-15) claims 1,4 page 8, line 10 - line 20	6
A	CH 486 498 A (KNAPSACK AKTIENGESELLSCHAFT) 28 February 1970 (1970-02-28)	
A	US 3 879 311 A (SCHOTT STUART ET AL) 22 April 1975 (1975-04-22) --- -/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

17 September 1999

Date of mailing of the international search report

29/09/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Thion, M

INTERNATIONAL SEARCH REPORT

National Application No
PCT/NL 99/00389

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category ²	Citation of document, with indication where appropriate, of the relevant passages	Relevant to claim No.
A	<p>EP 0 778 085 A (EKA CHEMICALS AB) 11 June 1997 (1997-06-11) -----</p>	

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/NL 99/00389

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 3804777	A	16-04-1974	CH 537210 A	13-07-1973
			DE 2136699 A	24-02-1972
			FR 2103247 A	07-04-1972
			GB 1308414 A	21-02-1973
			JP 51047675 B	16-12-1976
			NL 7110034 A	25-01-1972
			YU 191971 A,B	30-04-1979
FR 2325289	A	15-04-1977	NONE	
CH 486498	A	28-02-1970	BE 683856 A	16-12-1966
			DE 1243156 B	
			DE 1542257 A	16-04-1970
			DK 128269 B	01-04-1974
			FR 1510844 A	05-04-1968
			GB 1084159 A	
			LU 51465 A	06-09-1966
			NL 6609548 A,B	10-01-1967
			SE 328562 B	21-09-1970
			US 3488295 A	06-01-1970
US 3879311	A	22-04-1975	AU 6828174 A	30-10-1975
			BE 814275 A	28-10-1974
			CA 1018506 A	04-10-1977
			DE 2420374 A	07-11-1974
			FR 2227049 A	22-11-1974
			GB 1473217 A	11-05-1977
			IT 1010127 B	10-01-1977
			JP 50013292 A	12-02-1975
			NL 7405672 A	29-10-1974
EP 0778085	A	11-06-1997	CA 2191687 A	05-06-1997
			JP 9173872 A	08-07-1997
			NO 965069 A	05-06-1997